

Quality Paints since 1845  
**MATHYS®**



## MURFILL® WATERPROOFING COATING

# Long lasting elastic, waterproof wall protection

- 400 % Elastic
- Waterproof and water vapour permeable
- Excellent resistance against ageing in normal and industrial environment
- Protects reinforced concrete against carbonisation and corrosion
- Can be combined with Murfill® fleece for additional mechanical reinforcement and for bridging of

# MURFILL® WATERPROOFING COATING

## DESCRIPTION

An elastic, crack bridging and waterproofing façade coating. The microporous structure ensures that the base is constantly able to breathe. Ready for use and simple to apply on any façade. In other words: Façade protection with waterproof guarantees.

## RECOMMENDED USE

Coating and waterproofing of walls and façades.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,33 - 1,37 g/cm <sup>3</sup> (wit)
Gloss Level:	Semi-Matt
Gloss level at 60°:	8-10%
Gloss level at 85°:	13-16%
Solids Content in weight:	60 - 63%
Solids content in volume:	47 - 50%

## DRY TIMES BY 20° C/RV 50%

Touch dry:	45 minutes
Dry to handle:	± 8 hours
Dry to recoat:	24 hours
Fully cured:	± 2 days

## RECOMMENDED WET FILM THICKNESS

300 µm (coverage: 400 g/m<sup>2</sup>)

## RECOMMENDED DRY FILM THICKNESS

140 µm (coverage: 400 g/m<sup>2</sup>)

## THEORETICAL CONSUMPTION

- In combination with fleece > 1,3 kg/m<sup>2</sup>.
- 300 - 600 g/m<sup>2</sup> per coat depending on the application and the substrate.

## SURFACE PREPARATION

Murfill Waterproofing Coating can be applied directly on old (sound) paintwork after thorough brushing down. Chalking paints or substrates must be treated first with Primer 44HS or with Pegafix, when the old paint coat (acrylic paint or Murfill Waterproofing Coating) is affected by the solvents of Primer 44HS. New or unpainted substrates: on porous materials apply first a coat of Primer 4HS or Pegafix. On smooth non-porous substrates apply a coat of Pegalink white or a coat of Noxyde (except for white) diluted with 25% water. For stain, graffiti blocking and/or very fast recoating on all substrates, use Zinsser primers Bulls Eye 123 or 123 Plus, or Cover-Stain. Cracks < 0.5 mm wide: fill up with Murfill Waterproofing Coating. Cracks > 0.5 mm wide: fill up with Elastofill or Mur-Filler. Active cracks must be bridged with Murfill fleece.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

Minimum temperature: 5°C / Maximum 80% R.H.

## APPLICATION & THINNING: BRUSH

Do not dilute and apply in thick coat.

## APPLICATION & THINNING: ROLLER

Do not dilute and apply in thick coat.

## APPLICATION & THINNING: AIRLESS SPRAY

- If necessary, dilute with 2 - 5% water.
- Nozzle: 18 - 23 / Pressure: 200 bars.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not possible.

## CLEANING OF EQUIPMENT / SPILLS

Water.

## SAFETY DATA

VOC level:	25 g/l max.
VOC category:	A/i
VOC limit:	140 g/l (2007) / 140 g/l (2010)
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 05/11/2021

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)